

## SPECIFICATION NORDIC BRASS

CuZn15

EN CW502L

### Dimension:

Width range max 1000 mm

Thickness range 0,5...2,0 mm

Coils max. 3500 kg

Sheet length max 6000mm

### Chemical Composition %:

Copper (Cu) 84,0...86,0

Zinc (Zn) 14,0...16,0

### Physical properties:

Density abt 8.8 kg/dm<sup>3</sup>

Thermal expansion  $18 \cdot 10^{-6}$  1/K ( $\Delta T$  100°C = 1,8mm/m)

Specific heat 375 J/kg K

Thermal conductivity 160 %W/Cm

## Mechanical properties:

The material fulfils the requirements of standard EN 1172:2011(E)

Table 2 — Mechanical properties

Designation		Material condition	Tensile strength		0,2 % proof strength		Elongation	Hardness	
Material	Number		$R_m$		$R_{p0,2}$		$A_{50mm}$	HV	
Symbol			N/mm <sup>2</sup>		N/mm <sup>2</sup>		%	min.	max.
			min.	max.	min.	max.	min.	max.	
Cu-DHP CuZn0,5	CW024A CW119C	R220	220	260	—	140	33	—	—
		H040	—	—	—	—	—	40	65
		R240	240	300	140	—	8	—	—
		H065	—	—	—	—	—	65	95
		R290	290	—	250	—	—	—	—
		H090	—	—	—	—	—	90	—
CuSn0,15	CW117C	R250	250	320	200	—	9	—	—
		H060	—	—	—	—	—	60	90
		R300	300	370	250	—	4	—	—
		H085	—	—	—	—	—	85	110
CuAl5Zn5Sn1	CW309G	R400	400	—	170	—	45	—	—
		H080	—	—	—	—	—	80	—
CuSn4	CW450K	R290	290	390	—	190	40	—	—
		H070	—	—	—	—	—	70	100
CuZn15	CW502L	R310	310	370	200	290	10	—	—
		H090	—	—	—	—	—	90	115

## Fabrication properties:

Formability	Excellent
Soldering	Excellent
Brazing	Excellent
TIG	Good
MIG	Good
EBW	Poor

Brazing can lead to evaporation of zinc

## Typical use

Architecture, eg. roofing, facades, window and door frames, decoration